



**Barloworld**  
Plascon South Africa

# CARBOLINEUM WOOD PRESERVER

(Reg. No. L 932 Act/Wet 36 1947)

TECHNICAL DATA SHEET NO.: **M-8-D**  
DATE: **OCTOBER 2005**

**PRODUCT CODE: FPR 12**

THIS SUPERSEDES ALL PREVIOUS PUBLICATIONS

<b>Product Description</b>	<ul style="list-style-type: none"><li>• A modified creosote preserver for the protection of exterior timber. Contains active ingredient creosote (700 g/ℓ).</li></ul>		
<b>Intended Uses</b>	<ul style="list-style-type: none"><li>• A ready for use wood preserver for protection against fungal decay and attack by termites and wood boring insects. <b>CARBOLINEUM WOOD PRESERVER</b> is non-corrosive, not readily flammable and does not leach out.</li></ul>		
<b>Product Information</b>	Appearance	Matt	
	Colour	Dark brown to black	
	Solids	Approx. 98,5 % by mass; 98 % by volume	
	Viscosity at 23 °C	24 " FC4 (typical)	
	S G	1,000 (typical)	
	Flash Point	98 °C	
<b>Application Details</b>	Substrate	Well prepared wood surfaces.	
	Method	Brush, spray or dip.	
	Thinner	Not normally necessary - use <b>MINERAL TURPENTINE (AZH 1)</b> if required.	
	Thinning ratio	Ready for use by brush, spray or dip application.	
	Cleaning	<b>MINERAL TURPENTINE (AZH 1).</b>	
	Application Environment	Surface Temperature	Ambient Temperature
		Min.: 5 °C	Min.: 10 °C
		or 2 °C min. above dew point	
		Max.: 40 °C	Max.: 40 °C
		Max.: 85 %	
	Drying time	Dry to handle 16 h at 23 °C	
<b>Storage and Packaging</b>	Store away from direct sun, open flames, sparks and severe cold.		
	Packaging:	5 ℓ	

## CARBOLINEUM WOOD PRESERVER

<b>Surface Preparation</b>	<ul style="list-style-type: none"> <li>Timber must be dry, free from bark, decay, insect damage, ringshakes and foreign matter of any description.</li> <li>Cutting, shaping and working of the timer must be done before applying <b>CARBOLINEUM WOOD PRESERVER</b>.</li> </ul>
<b>Recommended Primer</b>	<ul style="list-style-type: none"> <li>No primer required.</li> </ul>
<b>Application</b>	<ul style="list-style-type: none"> <li>Suitable as supplied for application by brush, spray or dip.</li> <li>Apply copiously in one or more coats until wood is saturated. Where poles are to be set in the ground it is advisable to stand ends in <b>CARBOLINEUM WOOD PRESERVER</b> for several days to ensure maximum impregnation.</li> <li>Wash equipment with <b>MINERAL TURPENTINE (AZH 1)</b> immediately after use.</li> </ul>
<b>Warnings</b>	<ul style="list-style-type: none"> <li>Do not apply to surfaces that come into direct contact with food or feedstuffs.</li> <li>Store away from food and feedstuffs.</li> <li><b>CARBOLINEUM WOOD PRESERVER</b> has a strong, long-lasting smell and is extremely dark in colour.</li> <li>Even after prolonged drying, decorative paints or varnish must not be used over <b>CARBOLINEUM WOOD PRESERVER</b>. Only a bituminous aluminium system may be applied.</li> <li>Do not use on seats, benches or tables as staining of clothing is likely.</li> <li>Toxic to birds and fish.</li> <li>Keep water out of <b>CARBOLINEUM WOOD PRESERVER</b>.</li> </ul>
<b>Safety Precautions</b>	<ul style="list-style-type: none"> <li>Avoid inhalation of fumes and excessive or prolonged skin contact. Use suitable respirator and gloves. Wash with soap and water after use.</li> <li>If eyes are contaminated, flush with clear water for 15 minutes.</li> <li>Ensure adequate ventilation whilst applying.</li> <li>Prevent contamination of eating utensils, water, rivers, etc. with <b>CARBOLINEUM WOOD PRESERVER</b> or mineral turpentine used for cleaning equipment.</li> <li>Destroy empty container and do not re-use for any other purpose.</li> <li>Keep out of reach of children.</li> <li>Refer to Material Safety Data Sheet for complete information.</li> </ul>

### **DISCLAIMER:**

The recommendations contained herein are given in all good faith and are meant to guide the specifier or the user. They are based on results gained from our tests and experiences and are believed to be reliable. No guarantee is implied by the recommendations contained herein since conditions of use, method of application and cleanliness of the substrate prior to painting are beyond our control.

**N.B.:** Technology may change with time necessitating changes to this Technical Data Sheet (TDS). It is the responsibility of the user to ensure that the latest TDS is being used.

**NB: TO ORDER: Quote product name, product code number, packaging and colour.**

**BARLOWORLD PLASCON SOUTH AFRICA (PTY) LIMITED**

#### **CAPE TOWN:**

P O Box 42  
Eppindust 7475  
Tel: (021) 505-2400  
Fax: (021) 534-3791

#### **DURBAN:**

Private Bag X16  
Mobeni 4060  
Tel: (031) 451-3200  
Fax: (031) 451-3411

#### **MOGALE CITY**

**(KRUGERSDORP):**  
Private Bag X4010  
Kenmare 1745  
Tel: (011) 951-4500  
Fax: (011) 955-4136

#### **PORT ELIZABETH:**

P O Box 1594  
Port Elizabeth 6000  
Tel: (041) 401-1400  
Fax: (041) 453-4596